

# Product Data Bulletin

DOL 1000 Gloss Clear Cast Vinyl (Revision 4)

Dated: 12/04/01

## Description:

Avery Dennison™ DOL 1000 Gloss Clear Cast Vinyl is a premium quality, flexible, high gloss vinyl film designed for use as a protective overlamine film for screen printed and digital printed decals. DOL 1000 Gloss films offer exceptional value for applications requiring glossy colors and durability.

## Construction:

<b>Face Film:</b>	2.1 mil (53 mm) clear, high gloss, premium, cast vinyl film
<b>Adhesive:</b>	S-652 permanent, clear, acrylic, pressure-sensitive
<b>Release Liner:</b>	78# Bleached Kraft

## Physical Properties:

The following information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. They are given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material for his/her specific purpose. (Data represents averages and is not intended for use as a specification).

<b>Outdoor Durability:</b>	Up to 5 years when properly processed and applied (vertical exposure, unprinted film). Reference IB #5.30.		
<b>Minimum Surface/Ambient Air Application Temperature:</b>	40° F (5° C)		
<b>Application Surface:</b>	Flat, Flat with Rivets		
<b>Service Temperature Range:</b>	-40° F to 180° F (-40° C to 82° C) (Reasonable range of temperatures which would be expected under normal environmental time and temperature conditions)		
<b>Typical Film Caliper (w/adhesives):</b>	3.1 mils (79 µm)		
<b>Chemical Resistance:</b>	Resistant to most petroleum based oils, greases and aliphatic solvents. Resistant to mild acids, alkalies, salts		
<b>Typical Adhesion Values:</b>	<b>180° Peel</b>		
	<i>Substrate</i>	<i>15 min</i>	<i>24 hrs</i>
	<i>Stainless Steel</i>	<i>3.0 lb/in</i>	<i>4.0 lb/in</i>
		<i>(525 N/m)</i>	<i>(700 N/m)</i>
	<i>NOTE: Tested per ASTM 1000. Always pre-test your specific substrate prior to actual application.</i>		
<b>Shelf Life:</b>	One year when stored at temperatures and humidity conditions, 73° F (23° C) 50±5% R. H.		
<b>Tensile at Yield:</b>	4.0 to 8.0 lb/in. <sup>2</sup> (0.3 to 0.6 kg/cm <sup>2</sup> )		
<b>Elongation:</b>	100% minimum		



# Product Data Bulletin

<b>Dimensional Stability:</b>	Less than 0.015 in. (0.4 mm) shrinkage determined by shrinkage of unprinted film applied to 36 in. <sup>2</sup> (232 cm <sup>2</sup> ) aluminum test panel after 72 hours aging at 73° F (23° C) 50±5% R.H. followed by 48 hours at 150° F (65° C)
-------------------------------	--

*Revisions have been italicized.*

Avery Dennison™ is a registered trademark of Avery Dennison Corp.

*WARRANTY: All statements, technical information and recommendations about Avery Dennison products are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that Purchaser has independently determined the suitability of such products for its purposes. Avery Dennison products are warranted to be free from defects in material and workmanship for either one year (or the period stated on the specific product information literature in effect at time of delivery, if longer) from date of shipment if said product is properly stored and applied. It is expressly agreed and understood that Avery Dennison's sole obligation and Purchaser's exclusive remedy under this warranty, under any other warranty, express or implied, or otherwise, shall be limited to repair or replacement of defective product without charge at Avery Dennison's plant or at the location of product (at Avery Dennison's election), or in the event replacement or repairs is not commercially practical, to Avery Dennison's issuing Purchaser a credit reasonable in light of the defect in the product.*

*Avery Dennison's liability for defective products shall not exceed the purchase price paid therefore by Purchaser and in no event shall Avery Dennison be responsible for any incidental or consequential damages whether foreseeable or not, caused by defects in such product, whether such damage occurs or is discovered before or after replacement or credit, and whether or not such damage is caused by Avery Dennison's negligence.*

*NO EXPRESS WARRANTIES AND NO IMPLIED WARRANTIES, WHETHER OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR USE, OR OTHERWISE (EXCEPT AS TO TITLE), OTHER THAN THOSE EXPRESSLY SET FORTH ABOVE WHICH ARE MADE EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, SHALL APPLY TO PRODUCTS SOLD BY AVERY DENNISON. AVERY DENNISON SPECIFICALLY DISCLAIMS AND EXCLUDES ALL OTHER SUCH WARRANTIES. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND MANUALLY SIGNED BY AN OFFICER OF AVERY DENNISON.*

